

## INSTRUCTION GUIDE



To ensure maximum performance of Eco Release from storage through application, we recommend the following procedures:

### APPLICATION

- Read all current product information, labels and safety data before use.
- Mix well prior to decanting.
- Dilute concentrate with water to desired ratio, dependent on surface/use.
- Clean surface of any dust or debris and let dry.
- Apply a thin even coat to the surface with a quality sprayer. For best results, ER should be applied starting at the bottom and moving upwards to avoid drips. When used as a bond breaker, apply to the top of the cured panel in 2 even diagonal opposing coats.
- Smaller equipment may be dipped. Application via rag or brush is also optional.
- Clean up excess product with a rag.
- Allow approximately 10-15 minutes until dry, milky film should disappear and become translucent.
- Allow 24 hours until fully cured.

In extreme heat, the surface can be sprayed with water before applying Eco Release. Should weather conditions turn wet, merely check for waxy surface and judge if further application is required. Should you require to protect glass, mirrors or clear plastic, allow drying time and remove all excess. Continued use on formwork leaves surface clean after stripping; no cleaning required between pours, simply spray, pour, strip and repeat. For best results particularly on steel, aluminium or plywood, apply to the horizontal before erection.

**Formwork release or precast mould agent** - mix @ 1:4 parts water (non-porous surface) or 1:2 parts water (semi-porous surface).

**Protective coat for machinery and equipment** - mix @ 1:4 parts water.

## REMOVAL

---

Eco Release is made to naturally degrade during the curing process of concrete. However, if removal is required, use any alkaline cleaner and brush or a high-pressured washer.

## STORAGE & TRANSPORT

---

Eco Release is classified as a Non-Dangerous Good. Eco Release must be stored in a cool, dry, well ventilated area and kept out of reach of children. The shelf life is virtually indefinite if kept sealed in recommended conditions.

## SAFETY INSTRUCTIONS

---

If contact is made with your skin or eyes, rinse with water.

In the event of a spillage, mop up the area as the floor may be slippery. Rinse with water.

See current MSDS for full instructions.

*Note: The data and advice given apply only when the product is used for the stated application or applications. The product is not sold as suitable for any other application. Use of the product for applications other than as stated in this sheet may give rise to risks not mentioned in this sheet for which Mev-Aus Pty Ltd takes no responsibility*

*Mev-Aus Pty Ltd makes no warranty with respect to the performance of the product after it is applied by the purchaser, and the purchaser assumes all risks associated with the use or application of the product.*

Updated Oct 2020

Contact Novatec Formwork Systems for further product information or to view our Terms and Conditions.